

#8 Pea Gravel

Sieve: *ASTM C33*

Size	% Passing
1/2"	100
3/8"	85-100
#4	10-30
#8	0-10
#16	0-5
#200	<1.0

General Quality Results:

Bulk Specific Gravity SSD	ASTM C127	2.60
Absorption %	ASTM C127	0.9
Soundness MgSO4	ASTM C88	4.5
L.A. Abrasion & Impact	ASTM C131	37

Available Locations:

Bromley Lakes
14585 Brighton Road
Brighton, Co 80601

Contact Information:

Wade Raitz, Sales Representative
wade.raitz@boral.com
Cell: 303-638-3598